

AquaTutor®
waterproofers

GRIGOFLEX

Waterproof coating, bi-component and flexible, based on cement and acrylic polymers, for the treatment of concrete structures and masonry



Product description

AquaTutor® GRIGOFLEX is a premixed powder which, mixed with AquaTutor® GRIGOFLEX Comp. B, results in a waterproof coating with high adhesion to the surface, flexibility and permeability to water vapor.

AquaTutor® GRIGOFLEX is mainly used for the treatment of: tanks, water purifiers, swimming pools, aqueducts, canals, elevator shafts, earth dams, basements, locker rooms, showers, balconies, terraces, etc.

AquaTutor® GRIGOFLEX should be applied in two layers with a scrubbing brush, spatula or brush and can be used vertically and horizontally to ensure a perfect seal in thrust and counter-thrust. In the presence of cracks is strongly recommended the use of a reinforcement, fiberglass alkali-resistant mesh, interposed between two layers.

AquaTutor® GRIGOFLEX is available as a 34 kg. kit (25 kg. of powder and 9 kg. of liquid).

Supply and Storage

Packaging: 25 kg. bag/ 9 kg. canister



Surface Preparation and Application

Verify the conditions of the surface: cast sparys, gravel nests, cracks, holes for bolts of molds and surface defects, must be sealed, shaved and/or plastered with GALILEO ISI RAPID.

The surfaces to be treated should appear structurally sound and well cleaned from dust, oil, grease, efflorescence, and usually from all materials which may affect adherence (disarming of molds).

For cleaning, it is recommended to use systems such as sand-blasting, water-blasting or water under pressure (pressure washer).

In the case of old structures to be restored, it is recommended the demolition of existing material at the corners and/or connection areas between vertical walls and flooring and replace it with GALILEO ISI RAPID by creating a concave surface which can accommodate the AquaTutor® GRIGOFLEX.

AquaTutor® GRIGOFLEX should be mixed with a power drill at low revs.

Always pour the water first and then the powder, mix for about 3-5 minutes until obtaining a creamy mixture, free of lumps. Allow the dough to rest for about 5 minutes to allow for proper dispersion of the polymer.

Fully soak the surface with clean water and then remove the water in excess. AquaTutor® GRIGOFLEX may be applied by scrubbing brush, trowel or brush in two layers, after the hardening of the first one, to a maximum total thickness of about 3-4 mm.

After having installed the first layer, stretch and embed a fiberglass alkali-resistant mesh.

In the case of the closed structures with limited ventilation, remove any traces of condensation.

In the impermeability of balconies and terraces for ceramic laying on AquaTutor® GRIGOFLEX, use GrigoKoll® line products.

Technical data

Max. application thickness	3-4 mm
Mixing ratio	powder:liquid = 2,80:1 bag:canister = 1:1
Impermeability to water (1.5 atm. per 7 days in positive slope) UNI EN 12390/8 mod.	waterproof
Capillary absorption and water permeability (EN 1062-3)	$w < 0,04 \text{ kg/m}^2\text{h}^{0.5}$
Elongation at break (after 28 days at 23°C and 60% relative humidity):	> 15%
Water vapor permeability coefficient	$\mu < 250 / s_d < 2 \text{ m}$
CO2 dispersal coefficient	Not measurable
Fresh volume mass	1650 kg/m³
Adhesion to concrete (after 28 gg with temperature 23°C and 60% U.R.) according to EN 1542	> 0,5 MPa
Pot life	> 45 min.
Curing time	> 3h
Carbon dioxide permeability (CO2)	$S_D > 200 \text{ m}$
Reaction to fire	class E
Static Crack-bridging according to EN 1062-7	class A3 (> 0,5 mm)
Dinamic Crack-bridging according to EN 1062-7	class B1-B2 (no rupture of the specimen after 1000 cracking cycles with slit movements from 0,10 to 0,30 mm)
Permeability to water vapor - equivalent air thickness SD (m) according to EN ISO 7783-1	$S_D = 1,47 \text{ m}$ $\mu = 638$
Consumption	approx. 1,7 kg./sqm. per mm. of thickness

For structure which come in contact with aggressive waters (durability in °F), acid substances (pH), high temperatures (°C) and surfaces in the presence of efflorescence or sulphates, please contact the Technical Department of Fornaci Calce Grigolin S.p.A.

Disclaimers

Do not apply AquaTutor® GRIGOFLEX at temperatures below 5°C and above 30°C, or which might go below 5°C within the next 24 hours. In normal conditions, wait for at least 7 days before contact with the water. Avoid contact with hydrocarbons.

v. 11/2017

Numero Verde
800 350907

www.fornacigrigolin.it
info@fornacigrigolin.it

Grigolin
evoluzioni costruttive

The reported data refers to Quality Control tests in standard environmental conditions. Practical applications in the construction sites may detect significantly changed data, depending on operating conditions, so the information on the Card is only indicative because the user must always check its suitability for intended use of the product by taking responsibility for the use. Fornaci Calce Grigolin S.p.A. reserves the right to make technical changes of any kind without prior notice.