

binders

CEMENTO

Type II/A-LL 32.5 R
Type II/B-LL 32.5 R



Product description

Hydraulic binder for construction, obtained from ground Portland clinker, natural limestone and gypsum; with average compressive strength at 28 days, on plastic mortar, superior to 32.5 N/mm².

Supply and Storage

The CEMENTO type II/B-LL 32.5 R is supplied in bags on stretch pallets or in bulk. Store in a cool, dry and non ventilated place. Keep packaging intact. Use before expiry date stamped on the bag.



Quality and Service

The balanced and constant composition is ensured by an production plant with automatic dosage and daily controls in the laboratory. Skilled technical staff is available to provide on-site assistance and provide any useful advice for various applications. Controlled at point of origin, according to the UNI EN 197/1 Standard.

Fields of use

Concrete, even prefabricated, simple or reinforced, with good initial resistance, in not overly aggressive environments. Concrete for industrial flooring and road surfaces or for certain products (self-blocking, cords and blocks).

Technical data according to UNI EN 197/1 Standard

	Type II/A-LL 32.5 bulk	Type II/B-LL 32.5 v bag
Sulfates (such as SO ₃)	≤ 3,5%	≤ 3,5%
Chlorine	≤ 0,10%	≤ 0,10%
Time of curing start	≥ 75 min.	≥ 75 min.
Resistance to compression at 2 days	≥ 10 N/mm ²	≥ 10 N/mm ²
Resistance to compression at 28 days	≥ 32,5 N/mm ²	≥ 32,5 N/mm ²

Disclaimers

Avoid humid environments.