




BASEFORTE® REMAS

Silicates based consolidator for cement screeds.



Product description

Stabilizer/consolidator with dust-proof, silicates based for cement screeds. BASEFORTE® REMAS penetrates deeply and brings high resistance to the back surface, increasing the cohesion of the floor in all its thickness, including the superficial level.

Fields of use

BASEFORTE® REMAS is particularly indicated for:

- cement based back surfaces consolidating treatment, it confers high mechanical resistance
- perfect as anti-dust treatment
- to use with dusty screeds or poor in binder

Surface Preparation

BASEFORTE® REMAS must be applied on dry, fats, oils and paints free surfaces so to allow a perfect deep penetration of the product into the surface.

BASEFORTE® REMAS

Product application

The product can be used as it is or diluted at maximum ratio 1:1 in case it is required to increase the penetration into the back surface.

BASEFORTE® REMAS has to be applied with brush or roller, also in more coats, till final absorption.

Avoid the application of BASEFORTE® REMAS until denial, because it could create a very smooth surface with low absorption and difficult to cover.

For this reason it is necessary to pay special attention to let the product be absorbed without superficial stagnation. It is advised to make in jobsite an application test, to verify the surface absorption and individuate the correct dilution. Eventual succeeding layers must be done after complete drying of the product.

Parquet laying:

wait for more than 48 hours and in any case only when the humidity degree is lower than 2%. In case of heating floor the residual humidity must be equal or lower than 1,7%. In both cases the values must be ascertained with carbide hygrometer (UNI 11371).

Furthermore, the screed mechanical suitability must be verified by measuring the resistance to parallel to floor stress (UNI 10827).

It is advised to clean the tools soon after use.

Additional notes

Do not use BASEFORTE REMAS on:

- Absorbing or wet surfaces
- Anhydrite base screeds
- Self-levelling screeds
- Gypsum based surfaces

Avoid contact with glass, marble and natural stones surfaces.

Supply and storage

BASEFORTE® REMAS is supplied in 25 kg tank.

Warnings

Keep the product in its original tank with labels. It irritates eyes and skin, use suitable protection means. In case of accidental contact with eyes wash immediately with abundant water.

Professional use only. Use the product following the indications given in the technical datasheet and on the labels. During curing avoid thermal shocks and air currents. Protect the product from frost. Do not use BASEFORTE RE- MAS with temperatures lower than +5°C and higher than +30°C. Do not apply on frozen surfaces.

It is also advised to consult the safety datasheet of the product and to keep it always available for the professional applicators.

For further information please contact our technical support.

The reported data refers to Quality Control tests in standard environmental conditions. Practical applications in the construction sites may detect significantly changed data, depending on operating conditions, so the information on the Card is only indicative because the user must always check its suitability for intended use of the product by taking responsibility for the use. Fornaci Calce Grigolin S.p.A. reserves the right to make technical changes of any kind without prior notice.

BASEFORTE® REMAS

TECHNICAL DATA	RESULTS
Appearance	thick liquid
Specific weight	1,375 kg/l \pm 0,005
pH	12,75 \pm 0,5
Dry residual	35%
Overlaying time	24-48 h
Consumption	approx. 400-1000 g/m ² according to surface absorption

v. 07/2020

The reported data refers to Quality Control tests in standard environmental conditions. Practical applications in the construction sites may detect significantly changed data, depending on operating conditions, so the information on the Card is only indicative because the user must always check its suitability for intended use of the product by taking responsibility for the use. Fornaci Calce Grigolin S.p.A. reserves the right to make technical changes of any kind without prior notice.